

PRECONTRAI[®] 602

PRECONTRAI[®] 602 OPAQUE

WIDTH: 250/267 cm	WEIGHT: 650 g/sqm
JUMBO ROLLS*: ± 350 lm	LENGTHS*: ± 50 lm

WIDTH: 250/267 cm	WEIGHT: 750 g/sqm
JUMBO ROLLS*: ± 300 lm	LENGTHS*: ± 50 lm



STORAGE BUILDINGS



TEMPORARY BUILDINGS



WALKWAYS

G U A R A N T E E S A N D L A B E L S



ADVANTAGES

➤ FERRARI[®] PRÉCONTRAI[®] TECHNOLOGY:

- EXCEPTIONAL DIMENSIONAL STABILITY
- EXCELLENT WELDABILITY
- HIGH DURABILITY


➤ OPTIMUM WEIGHT/CAPACITY RATIO (602 OPAQUE)

➤ ACCESSORIES: PRÉCONTRAI[®] 709 (p. 77) FERRARI[®] KEDER (p. 78)


➤ MAINTENANCE: FERRARI[®] CLEAN (p. 81)

COLOURS & REFERENCES


(COLOURS ARE INDICATIVE)



Ref. 602-8100



Ref. 602-8503 (opaque)



Ref. 602-8504 (opaque)

TECHNICAL SPECIFICATIONS

	PRÉCONTRAI [®] 602	PRÉCONTRAI [®] 602 OPAQUE	STANDARDS
YARN	1100 dtex PES HT	1100 dtex PES HT	TERSUISSE
WEIGHT	650 g/sqm	750 g/sqm	EN ISO 2286-2
WIDTH	250/267 cm	250/267 cm	
TENSILE STRENGTH (WARP/WEFT)	250/250 daN/5 cm	250/250 daN/5 cm	EN ISO 1421
TEAR STRENGTH (WARP/WEFT)	20/20 daN	20/20 daN	DIN 53.363
ADHESION	9/9 daN/5 cm	9/9 daN/5 cm	EN ISO 2411
FINISH	VARNISH BOTH SIDES	VARNISH BOTH SIDES	
FLAME RETARDANCY	M2/NFP 92-507 • B1/DIN 4102-1 • M2/UNE 23.727		
HANDLING TEMPERATURE RANGE	-30°C/+70°C	-30°C/+70°C	
QUALITY MANAGEMENT SYSTEM			ISO 9001

The technical characteristics shown are average values given as a guide and may be modified.

*Our packaging data are given for information only and may vary as a function of manufacturing conditions.